



Armourscreed® AS50 BP04a

Crack Repairs & Performance Joints



MATERIAL SAFETY DATA SHEET

1/4

PRODUCT: Armourscreed 50 / 100

OTHER NAMES: Dantex Maxiflex 50 / 100, Armourscreed Basecoat, AS50, AS100, Stress Absorbing Inlaid Cracksealing System

STOCK CODES: BP04, BP04AB, BP04ARINGWAY

1. SUBSTANCE / PREPARATION & COMPANY IDENTIFICATION:

CHEMICAL NATURE: Fibre reinforced polymer modified bituminous material.

COMPANY: Walker Sealants Limited
Outland Head Works
Hope Valley, Bradwell
Derbyshire, S33 9JP

TEL: +44 (0)1433 621 600

EMAIL: sales@walkersealants.co.uk

WEB: www.walkersealants.co.uk

2. COMPOSITION / INFORMATION ON INGREDIENTS:

CONTAINS	EEC SYMBOL	R & S PHRASES	CAS NUMBER
SBS Polymers	Not Classified		106107-54-4 9003-55-8
Bitumen	Not Classified		8052-42-4 9003-55-8

3. HAZARD IDENTIFICATION:

None

4. FIRST AID MEASURES:

In all cases if symptoms are severe, persist or cause concern obtain immediate medical advice. First aid procedures apply when the product is at elevated temperature.

INHALATION: Move the affected person to fresh air. If the person feels unwell or in case of prolonged exposure, seek medical attention.

EYES: Rinse with copious amounts of cold water for at least 10 mins and seek medical attention immediately.

SKIN: Treat the affected area with water - spray or immersion. Do not attempt to remove product from skin. Seek medical advice immediately.

INGESTION: Rinse mouth with water. If swallowed drink water in small amounts. Do not induce vomiting. Seek medical attention immediately.



MATERIAL SAFETY DATA SHEET *continued*

5. FIRE FIGHTING MEASURES:

SUITABLE EXTINGUISHING MEDIA: Carbon Dioxide, Dry Chemicals, Foam, Water Spray mist

UNSUITABLE EXTINGUISHING MEDIA: High Pressure Water Jet

EXPOSURE HAZARDS: Risk of Fire and Explosions if product is overheated.

THE MATERIAL REACTS VIOLENTLY WITH WATER.

PROTECTIVE EQUIPMENT: Use full protective clothing and self-contained breathing apparatus.

6. ACCIDENTAL RELEASE MEASURES:

PROTECTIVE MEASURES: Avoid contact with skin, eyes and clothing. Wear suitable protective clothing
 Enclosed spaces should be opened to atmosphere.

CLEAN UP METHODS:

Soil Allow the material to solidify

Water The product has a density greater than 1.00g/cm³, contain and recover by physical means.
 Dispose safely in accordance with local or national regulations.

7. HANDLING & STORAGE:

HANDLING: Hot Material (170 - 190°C) - Avoid breathing fumes. Ensure adequate ventilation. Avoid eye and skin contact. Wear suitable protective clothing (S36/37/39).

STORAGE: Packages - Store in a cool dry place away from sources of ignition. Hot Liquid - Ventilate adequately as Hydrogen Sulphide can accumulate in confined spaces.

8. EXPOSURE CONTROL / PERSONAL PROTECTION:

The level of protection and types of controls necessary will vary depending upon potential exposure conditions. Select controls based on a risk assessment of local circumstances. Appropriate measures include adequate ventilation to control airborne concentrations below the exposure guidelines/limits. PPE should meet recommended national standards. Check PPE suppliers.

EXPOSURE CONTROL LIMITS:

Petroleum Fumes	OES (8 hours) 5mg/m ³
	OES (15 minutes) 15mg/m ³
Hydrogen Sulphide	OES (8 hours) 10mg/m ³

Manufactures & Suppliers of:
 Joint Sealants
 Bituminous Repair Compounds
 High Friction Surfacing
 Colour Coated Aggregates
The Complete Highway Service

Walker Sealants Limited
 Manufacturing & Sales Division
 Outland Head
 Bradwell, Hope Valley
 Derbyshire, S33 9JP
 Tel: 01433 621 600



Directors: J.S. Walker, J.G.R. Walker
 Company Reg No. 4041871

A member of the Walker Group of Companies



MATERIAL SAFETY DATA SHEET *continued*

3/4

SBS Polymer
OES (15 minutes) 25mg/m³
OES (8 hours) 10mg/m³
OES (15 minutes) 25mg/m³

SKIN PROTECTION: Wear suitable long sleeved, full body overalls and safety boots at all times. Exposed skin must be covered due to risk from splashes.

HAND PROTECTION: Wear suitable gloves.

EYE PROTECTION: Wear suitable goggles or face protection.

9. PHYSICAL & CHEMICAL PROPERTIES:

APPEARANCE: SOLID FORM BLACK

FLASHPOINT: ≥ 250°C

ODOUR: PERCEPTIVE

IGNITION: 280°C

DENSITY RANGE: 1.80 ± 0.5g/cm³

MELTING POINT/RANGE: 120 - 190°C

SOLUBILITY IN WATER: INSOLUBLE

VISCOSITY:

10. STABILITY & REACTIVITY:

THERMAL DECOMPOSITION: Stable under normal operating conditions.

CONDITIONS TO AVOID: Overheating, Water Ingress.

MATERIALS TO AVOID: The hot produce reacts violently with water.

HAZARD DECOMPOSITION: Thermal decomposition or burning may release Carbon Monoxide, Soot and Hydrogen Sulphide.

11. TOXICOLOGICAL INFORMATION:

INGESTION: > 2000mg/kg* =

EYES: > 2000mg/kg*

* EXPECTED RESULTS, NOT TESTED

12. TRANSPORT INFORMATION:

NOT CLASSIFIED AS HAZARDOUS FOR TRANSPORT

13. DISPOSAL INFORMATION:

Armourscreed Material - authorised disposal in accordance with local or National Regulations.

Packages - to be considered as industrial waste, can be recycled if not contaminated.

14. ECOLOGICAL INFORMATION:

Avoid losses to the environment wherever possible. No known risks.



Armourscreed® AS50 BP04a

Crack Repairs & Performance Joints



MATERIAL SAFETY DATA SHEET *continued*

4/4

MOBILITY: **Air:** There is a slow loss by evaporation.
Soil: The product generally has a slow soil mobility.
Water: The product is not water soluble.

DEGRADABILITY: Non - Biodegradable.

ECOTOXICITY: Not dangerous for Aquatic or Terrestrial life.

96 HOURS LC50 (mg/L): Insoluble - Non-Toxic.

15. REGULATORY INFORMATION:

EC LABELLING AS REQUIRED BY CHIP*

SYMBOL(S) EC: Not classified according to EEC directives 67/548/EEC and 88/379/EC.

S36/37/39: Wear suitable protective clothing.

16. OTHER INFORMATION:

DOCUMENT REVISION DATE: March 2020 Revision 4

PRODUCT USE:

The provisions of Safety Data Sheets come under the REACH and CHIP regulations. This is in addition to the users of products supplied by Walker Sealants Limited should take appropriate measures to ensure working practices are in accordance with the Control of Substances Hazardous to Health (COSHH).

The information in the MSDS was obtained from sources believed to be reliable. The information is provided with no warranty, expressed or implied, regarding its correctness. The conditions or methods of handling, storage, use or disposal of the material are beyond our control and may be beyond our knowledge. For this and other reasons we assume no responsibility and expressly disclaim liability for loss, damage or expense arising from, or in any way connected with the handling, storage, use or disposal of this material.

This data is provided for your information and your attention is drawn to the appropriate package labelling and the product safety data sheet. Users of the product must ensure its proper use in accordance with good industrial practices, proper medical advice and any official or Government notice or publication. This information is provided gratuitously independent of any sale of the product and does not form part of any contract or sale nor does it constitute any representation, warranty or condition of merchantability or fitness for any purpose.

Manufactures & Suppliers of:
Joint Sealants
Bituminous Repair Compounds
High Friction Surfacing
Colour Coated Aggregates
The Complete Highway Service

Walker Sealants Limited
Manufacturing & Sales Division
Outland Head
Bradwell, Hope Valley
Derbyshire, S33 9JP
Tel: 01433 621 600



Directors: J.S. Walker, J.G.R. Walker
Company Reg No. 4041871

A member of the Walker Group of Companies